

537, 651

Rec'd 10/537651
T/PTO 08 JUN 2005

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization
International Bureau(43) International Publication Date
17 June 2004 (17.06.2004)

PCT

(10) International Publication Number
WO 2004/050239 A2

- (51) International Patent Classification⁷: **B01J 31/00**
- (21) International Application Number:
PCT/GB2003/005180
- (22) International Filing Date: 1 December 2003 (01.12.2003)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
0228267.1 4 December 2002 (04.12.2002) GB
- (71) Applicant (for all designated States except US): **JOHNSON MATTHEY PLC** [GB/GB]; 2-4 Cockspur Street, Trafalgar Square, London SW1Y 5BQ (GB).
- (72) Inventors; and
- (75) Inventors/Applicants (for US only): **LINDALL, Charles, Mark** [GB/AU]; 94 Pindari Avenue, Camden, NSW 2570 (AU). **SLACK, Neville** [GB/GB]; 139 Station Road, Billingham, Stockton-on-Tees, Cleveland TS23 2RL (GB). **PARTRIDGE, Martin, Graham** [GB/GB]; 33 Houghton Banks, Ingleby Barwick, Stockton-on-Tees, Cleveland TS17 5AL (GB).
- (74) Agents: **GIBSON, Sara, Hillary, Margaret et al.**; Intellectual Property Department, Johnson Matthey Catalysts, P.O. Box 1 Belasis Avenue, Billingham, Cleveland TS23 1LB (GB).
- (81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.
- (84) Designated States (*regional*): ARIPO patent (BW, GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).
- Published:**
— without international search report and to be republished upon receipt of that report
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.*

(54) Title: CATALYST AND PROCESS

(57) Abstract: A catalyst composition comprises the reaction product of an alkoxide or condensed alkoxide of a metal M, selected from titanium, zirconium, hafnium, aluminium, or a lanthanide, an alcohol containing at least two hydroxyl groups, a 2-hydroxy carboxylic acid and a base, wherein the molar ratio of base to 2-hydroxy carboxylic acid is in the range 0.01 - 0.79:1. The composition is useful as a catalyst for esterification reactions, especially for the production of polyesters such as polyethylene terephthalate, polytrimethylene terephthalate and polybutylene terephthalate.

WO 2004/050239 A2

CATALYST AND PROCESS

The invention concerns an esterification process and in particular an esterification process which utilises a novel organotitanium or organozirconium catalyst which is particularly suitable for use in the manufacture of polybutylene terephthalate.

- 5 Organotitanium compounds and, in particular, titanium alkoxides are known as catalysts for esterification processes. During the esterification, these compounds are frequently converted to polymeric compounds of titanium which result in a hazy product. The presence of a haze is a particular disadvantage in polyesters which have a high viscosity and/or high melting point and are therefore difficult to filter. Furthermore, many organotitanium compounds which are effective
- 10 catalysts in the manufacture of polyesters such as polyethylene terephthalate are known to produce unacceptable yellowing in the final polymer. Tetra(n-butyl)titanate (TNBT) is a widely used catalyst for the preparation of polybutylene terephthalate (PBT). TNBT is susceptible to hydrolysis which may lead to the formation of small amounts of solid hydrolysis products which can reduce the effectiveness of filtration equipment used in the manufacturing process.
- 15 In GB-A-2314081, an esterification catalyst comprising the reaction product of an alkoxide or condensed alkoxide of titanium or zirconium, an alcohol containing at least two hydroxyl groups, a 2-hydroxy carboxylic acid and a base. In that patent, the preferred amount of base for monobasic 2-hydroxy acids such as lactic acid, is in the range 0.8 to 1.2 mole per mole of 2-hydroxy acid. In the case of citric acid (a tribasic acid), the preferred amount is in the range 1 to 3 moles base per mole of
- 20 2-hydroxy acid. We have found that when a catalyst composition of the type described in GB-A-2314081 is made using 1,4-butane diol as the dihydric alcohol and an inorganic base is present in the preferred concentration range, the 1,4-butane diol forms a complex with the base leading to formation of a gelled product which is not suitable for use as a catalyst.

- 25 According to the invention we therefore provide a catalyst composition comprising the reaction product of an alkoxide or condensed alkoxide of a metal M, selected from titanium, zirconium, hafnium, aluminium, or a lanthanide, an alcohol containing at least two hydroxyl groups, a 2-hydroxy carboxylic acid and a base, wherein the molar ratio of base to 2-hydroxy carboxylic acid is in the range 0.01 – 0.79:1.

- 30 According to a further aspect of the invention, we also provide a process for the preparation of an ester comprising carrying out an esterification reaction in the presence of a catalyst comprising the reaction product of an alkoxide or condensed alkoxide of a metal M, selected from titanium, zirconium, hafnium, aluminium, or a lanthanide, an alcohol containing at least two hydroxyl groups, a 2-hydroxy carboxylic acid and a base, wherein the molar ratio of base to 2-hydroxy carboxylic acid is

in the range 0.01 – 0.79:1.

Preferred metals are titanium and zirconium.

The catalyst of the invention is the reaction product of a titanium, zirconium, hafnium, aluminium, or lanthanide alkoxide or condensed alkoxide, an alcohol containing at least two hydroxyl groups, a 2-hydroxy carboxylic acid and a base. Preferably, the alkoxide has the formula $M(OR)_x$ in which M is titanium, zirconium, hafnium, aluminium, or a lanthanide, R is an alkyl group and x is the valency of the metal M. More preferably R contains 1 to 6 carbon atoms and particularly suitable alkoxides include tetraisopropoxy titanium, tetra-n-butoxy titanium, tetra-n-propoxy zirconium, tetra-n-butoxy zirconium and aluminium tri-sec-butoxide.

- 5 The condensed alkoxides suitable for preparing the catalysts useful in this invention are typically prepared by careful hydrolysis of titanium or zirconium alkoxides and are frequently represented by the formula $R^1O[M(OR^1)_2O]_nR^1$ in which R^1 represents an alkyl group and M represents titanium, zirconium, hafnium, aluminium, or a lanthanide, preferably titanium or zirconium. Preferably, n is less than 20 and more preferably is less than 10. Preferably R^1 contains 1 to 6 carbon atoms and useful
15 condensed alkoxides include the compounds known as polybutyl titanate, polyisopropyl titanate and polybutyl zirconate.

- Preferably the alcohol containing at least two hydroxyl groups is a dihydric alcohol e.g. 1,2-ethanediol, 1,2-propanediol, 1,3-propanediol, 1,4-butane diol or a dihydric alcohol containing a longer chain such as diethylene glycol or a polyethylene glycol. Particularly preferred is 1,4-butane diol. The catalyst
20 can also be prepared from a polyhydric alcohol such as glycerol, trimethylolpropane or pentaerythritol. When the catalyst is intended for polyester manufacture, the alcohol containing at least two hydroxyl groups is preferably of a similar composition to that used in the polyesterification reaction.

- Preferably the catalyst is prepared by reacting a dihydric alcohol with an alkoxide or condensed
25 alkoxide in a ratio of from 2 to 12 moles of dihydric alcohol to each mole of the titanium or zirconium. More preferably the reaction product contains 4 to 8 moles dihydric alcohol per mole of metal M.

- Preferred 2-hydroxy carboxylic acids include lactic acid, citric acid, malic acid and tartaric acid. Some suitable acids are supplied as hydrates or as aqueous mixtures. Acids in this form as well as anhydrous acids are suitable for preparing the catalysts used in this invention. The preferred molar
30 ratio of acid to metal M in the reaction product is 1 to 4 moles (more preferably 1.5 to 3.5 moles) of 2-hydroxy acid per mole of metal M.

The base used in preparing the catalyst composition is generally an inorganic base and suitable

bases include aqueous solutions of salts of weak acids with metals selected from Group IA or IIA of the periodic table of elements or with zinc, aluminium, iron(II), copper(II), nickel, cobalt (II), manganese (II), lanthanum, cerium, neodymium, and samarium. Preferred bases include sodium hydroxide, potassium hydroxide, ammonium hydroxide, lithium hydroxide, sodium carbonate, magnesium hydroxide, calcium hydroxide, aluminium acetate, zinc oxide, caesium carbonate and ammonia. The molar ratio of base to 2-hydroxy carboxylic acid is in the range 0.05 to 0.79 : 1. In the case of citric acid (a tribasic acid), the preferred amount is in the range 0.01 to 0.6 moles base per mole of 2-hydroxy acid. In general, the amount of base present is usually in the range 0.05 to 2.4 moles (preferably from 0.5 to 2, especially 0.7 to 1.5 moles) per mole of metal M.

10 It is frequently convenient to add water together with the base when preparing the catalysts.

The catalyst can be prepared by mixing the components (alkoxide or condensed alkoxide, dihydric alcohol, 2-hydroxy acid and base) with removal of any by-product, (e.g. isopropyl alcohol when the alkoxide is tetraisopropoxytitanium), at any appropriate stage. In one preferred method the alkoxide or condensed alkoxide and dihydric alcohol are mixed and subsequently, 2-hydroxy acid and then base are added or a pre-neutralised 2-hydroxy acid solution, is added. In an alternative preferred method the alkoxide or condensed alkoxide is reacted with the 2-hydroxy acid and by-product alcohol is removed. Base is then added to this reaction product followed by a dihydric alcohol to produce the reaction product which is a catalyst of the invention. If desired, further by-product alcohol can then be removed by distillation. The catalyst may be diluted in a solvent, which is preferably the alcohol to be used in the esterification reaction. For example, if the catalyst is to be used for making polybutylene terephthalate, then the catalyst may be diluted in 1,4-butanediol.

The esterification reaction of the process of the invention can be any reaction by which an ester is produced. The reaction may be a direct esterification in which a carboxylic acid or its anhydride react with an alcohol to form an ester; or a transesterification (alcoholysis) in which a first alcohol reacts with a first ester to produce an ester of the first alcohol and a second alcohol produced by cleavage of the first ester; or a interesterification reaction in which two esters are reacted to form two different esters by exchange of alkoxy radicals.

Many carboxylic acids and anhydrides can be used in direct esterification including saturated and unsaturated monocarboxylic acids such as stearic acid, isostearic acid, capric acid, caproic acid, palmitic acid, oleic acid, palmitoleic acid, triacontanoic acid, benzoic acid, methyl benzoic acid and salicylic acid, dicarboxylic acids such as phthalic acid, isophthalic acid, terephthalic acid, sebacic acid, adipic acid, azelaic acid, succinic acid, fumaric acid, maleic acid, naphthalene dicarboxylic acid and pamoic acid and anhydrides of these acids and polycarboxylic acids such as trimellitic acid, citric acid, trimesic acid, pyromellitic acid and anhydrides of these acids. Alcohols frequently used for

direct esterification include aliphatic straight chain and branched monohydric alcohols such as butyl, pentyl, hexyl, octyl and stearyl alcohols and polyhydric alcohols such as glycerol and pentaerythritol. A preferred process of the invention comprises reacting 2-ethylhexanol with phthalic anhydride to form bis(2-ethylhexyl)phthalate.

- 5 The esters employed in an alcoholysis reaction are generally the lower homologues such as methyl, ethyl and propyl esters since, during the esterification reaction, it is usual to eliminate the displaced alcohol by distillation. Such esters of the acids suitable for direct esterification are used in the process of the invention. Frequently (meth)acrylate esters of longer chain alcohols are produced by alcoholysis of esters such as methyl acrylate, methyl methacrylate, ethyl acrylate and ethyl
- 10 methacrylate. Typical alcohols used in alcoholysis reactions include butyl, hexyl, n-octyl and 2-ethyl hexyl alcohols and substituted alcohols such as dimethylaminoethanol.

When the esterification reaction is a transesterification between two esters, generally the esters will be selected so as to produce a volatile product ester which can be removed by distillation.

- Polymeric esters can be produced by processes involving direct esterification or transesterification
- 15 and a particularly preferred embodiment of the process of the invention is a polyesterification reaction in the presence of the catalyst described hereinbefore. In a polyesterification reaction polybasic acids or esters of polybasic acids are usually reacted with polyhydric alcohols to produce a polymeric ester, often via a diester intermediate product. Linear polyesters are produced from dibasic acids such as those mentioned hereinbefore or esters of said dibasic acids and dihydric alcohols.
- 20 Alternatively, the preparation of polyesters may be achieved starting from an ester (typically a low alkyl ester) of a dicarboxylic acid, which may be e.g. a $C_1 - C_6$ alkyl ester of any of the di- or polycarboxylic acids mentioned above. Of these, methyl esters such as, in particular dimethyl terephthalate or dimethyl naphthalate, are preferred starting materials for the preparation of polyesters. Preferred polyesterification reactions according to the invention include the reaction of
- 25 terephthalic acid or dimethyl terephthalate with 1,2-ethanediol (ethylene glycol) to produce polyethylene terephthalate (PET), with 1,3-propane diol to form polypropylene terephthalate (also known as poly(trimethylene)terephthalate or PTT), or with 1,4-butanediol (butylene glycol) to produce polybutylene terephthalate (PBT) or reaction of naphthalene dicarboxylic acid with 1,2-ethanediol to produce polyethylene naphthalate (PEN). Other glycols such as 1,6-hexanediol, and pentaerythritol
- 30 are also suitable for preparing polyesters.

The catalyst and process of the present invention are particularly suitable for the preparation of PBT, PET or PTT by the reaction of terephthalic acid or an ester thereof with 1,4-butane diol, 1,3-propane diol or 1,2-ethane diol. We have found that the catalyst and process of the invention show numerous benefits compared with the known titanium alkoxide catalysts. For example, when used to make

PBT, the catalysts and process of the invention can produce a polymer with better filtration properties than the commonly used TNBT catalyst and that the rate of reaction is at least as fast and often faster than using TNBT.

5 A typical process for the preparation of polybutylene terephthalate comprises two stages. In the first stage dimethyl terephthalate is reacted with 1,4-butanediol to form a prepolymer and the by-product methanol is removed. The prepolymer is subsequently heated in a second stage under reduced pressure to remove 1,4-butanediol and form a long chain polymer. Either or both these stages may comprise a process according to this invention.

10 The esterification reaction of the invention can be carried out using any appropriate, known technique for an esterification reaction.

15 In direct esterification the acid or anhydride and an excess of alcohol are typically heated, if necessary in a solvent, in the presence of the catalyst. Water is usually the by-product of the reaction and this is removed, as an azeotrope with a boiling mixture of solvent and/or alcohol. Generally, the solvent and/or alcohol mixture which is condensed is immiscible with water which is therefore separated before solvent and/or alcohol are returned to the reaction vessel. When reaction is complete the excess alcohol and, when used, solvent are evaporated. In contrast to prior art esterification processes, it is not generally necessary to remove the catalyst from the reaction mixture. A typical direct esterification reaction is the preparation of bis(2-ethylhexyl) phthalate which is prepared by mixing phthalic anhydride and 2-ethyl hexanol. An initial reaction to form a monoester is fast but the subsequent conversion of the monoester to diester is carried out by refluxing in the presence of the catalyst at a temperature of 180-200°C until all the water has been removed. Subsequently the excess alcohol is removed.

25 In an alcoholysis reaction, the ester, first alcohol and catalyst are mixed and, generally, the product alcohol (second alcohol) is removed by distillation often as an azeotrope with the ester. Frequently it is necessary to fractionate the vapour mixture produced from the alcoholysis in order to ensure that the second alcohol is separated effectively without significant loss of product ester or first alcohol. The conditions under which alcoholysis reactions are carried out depend principally upon the components of the reaction and generally components are heated to the boiling point of the mixture used.

30 A preferred process of the invention is the preparation of polybutylene terephthalate. A typical batch production of polybutylene terephthalate is carried out by charging terephthalic acid and 1,4 butanediol to a reactor along with catalyst if desired and heating the contents to 170 - 210°C under a pressure of about 0.3 MPa. Reaction commences as the acid dissolves at about 230°C and water is

removed. The product is transferred to a second autoclave reactor and catalyst is added, if needed. The reactor is heated to 240 - 260°C under an eventual vacuum of 100 Pa to remove 1,4 butanediol by-product. The molten product ester is discharged from the reactor, cooled and chipped.

Conventional additives to polyesterification reactions, such as colour modifiers (e.g. cobalt compounds, pigments or dyes), stabilisers (especially those based on phosphorus compounds e.g. phosphoric acid or phosphate ester species), fillers etc may also be added to the polyester reaction mixture.

The amount of catalyst used in the process of the invention generally depends upon the metal content, expressed as elemental metal, of the catalyst. Usually the amount is from 30 to 1000 parts per million (ppm) on weight of product ester for direct or transesterification reactions. Preferably the amount is from 30 to 450 ppm on weight of product ester and more preferably 50 to 450 ppm on weight of product ester. In polyesterification reactions the amount used is generally expressed as a proportion of the weight of product polyester and is usually from 5 to 500 ppm expressed as metal based on product polyester. Preferably the amount is from 5 to 150 ppm expressed as metal, e.g. as Ti or Zr.

The process of this invention has been shown to effectively produce esters and polyesters at an economical rate.

The invention is illustrated by the following examples.

20 EXAMPLE 1 (Comparative)

Citric acid monohydrate (300g, 1.43 moles) was dissolved in warm water (209g) in a 1 litre fishbowl flask fitted with stirrer, condenser and thermometer. To the stirred solution was added slowly titanium isopropoxide (162g, 0.57 moles) (VERTEC™ TIPT) from a dropping funnel. A mixture of isopropanol and water was removed by distillation at about 80 - 85°C. The product was cooled to around 60°C and 32% wt/wt aqueous NaOH (214g, 1.71 moles) was added slowly by dropping funnel to the stirred solution. The resulting product was cooled, then mixed with 1,4-butanediol (411g, 4.56 moles) and heated under vacuum to remove isopropanol/water. The product formed a gel at this point.

EXAMPLE 2

30 Citric acid monohydrate (300.1g, 1.43 moles) was dissolved in warm water (209g) in a 1 litre fishbowl flask fitted with stirrer, condenser and thermometer. To the stirred solution was added slowly tetra(n-butyl)titanate (194g, 0.57 moles) (VERTEC™ TNBT) from a dropping funnel. A mixture of n-butanol and water was removed by distillation at about 80 - 85 °C under vacuum. The product was cooled to around 60 °C and 5% wt/wt aqueous NaOH (600g, 0.75 moles) was added slowly by dropping funnel
35 to the stirred solution. The resulting product was cooled, then mixed with 1,4-butanediol (411g, 4.56

moles) and heated under vacuum to remove n-butanol/water. The product was a clear mobile liquid.

EXAMPLE 3

Citric acid monohydrate (300g, 1.43 moles) was dissolved in warm water (209g) in a 1 litre fishbowl flask fitted with stirrer, condenser and thermometer. To the stirred solution was added slowly tetra(n-butyl)titanate (194.0g, 0.57 moles) from a dropping funnel. A butanol/water mixture was removed by distillation at about 80 – 85 °C under vacuum. The product was cooled to around 60 °C and 5% wt/wt aqueous NaOH (400g, 0.5 moles) was added slowly by dropping funnel to the stirred solution. The resulting product was cooled, then mixed with 1,4-butanediol (411g, 4.56 moles) and heated under vacuum to remove n-butanol/water. The product was a clear mobile liquid.

EXAMPLE 4

Citric acid monohydrate (300g, 1.43 moles) was dissolved in warm water (209g) in a 1 litre fishbowl flask fitted with stirrer, condenser and thermometer. To the stirred solution was added slowly tetra(n-butyl)titanate (194.0g, 0.57 moles) from a dropping funnel. A butanol/water mixture was removed by distillation at about 80 – 85 °C under vacuum. The product was cooled to around 60 °C and 5% wt/wt aqueous NaOH (400g, 0.5 moles) was added slowly by dropping funnel to the stirred solution. The resulting product was cooled, then mixed with 1,4-butanediol (634g, 7.05 moles) and heated under vacuum to remove n-butanol/water. The product was a clear mobile liquid.

EXAMPLE 5

Citric acid monohydrate (150g, 0.71 moles) was dissolved in warm water (104.5g) in a 1 litre fishbowl flask fitted with stirrer, condenser and thermometer. To the stirred solution was added slowly titanium isopropoxide (81.0g, 0.28 moles) from a dropping funnel. and an isopropanol/water mixture was removed by distillation at about 80 – 85 °C under vacuum. The product was cooled to about 60 °C and 5% wt/wt aqueous NaOH (200g, 0.25 moles) was added slowly by dropping funnel to the stirred solution. The resulting product was cooled, then mixed with 1,4-butane diol (206g, 2.28 moles) and heated under vacuum to remove isopropanol/water. The product was then filtered to provide a clear viscous liquid.

EXAMPLE 6

Citric acid monohydrate (150g, 0.71 moles) was dissolved in warm water (104.5g) in a 1 litre fishbowl flask fitted with stirrer, condenser and thermometer. To the stirred solution was added slowly tetra(n-butyl)titanate (97.0g, 0.28 moles) from a dropping funnel. A butanol/water mixture was removed by distillation at about 80 – 90 °C under vacuum. The product was cooled to about 60 °C and 5% wt/wt aqueous NaOH (200g, 0.25 moles) was added slowly by dropping funnel to the stirred solution. The resulting product was cooled, then mixed with 1,3-propanediol (174g, 2.28 moles) and heated under

vacuum to remove butanol/water. The product was then filtered to provide a clear viscous mobile liquid.

EXAMPLE 7

- 5 Citric acid monohydrate (150g, 0.71 moles) was dissolved in warm water (105g) in a 1 litre fishbowl flask fitted with stirrer, condenser and thermometer. To the stirred solution was added slowly tetra(n-butyl)titanate (97.0g, 0.28 moles) from a dropping funnel. A butanol/water mixture was removed by distillation at about 80 – 90 °C under vacuum. The product was cooled to about 60 °C and 10% wt/wt aqueous NaOH (100g, 0.25 moles) was added slowly by dropping funnel to the stirred solution.
- 10 The resulting product was cooled, then mixed with 1,3-propanediol (173.5g, 2.28 moles) and heated under vacuum to remove butanol/water. The product was then filtered to provide a clear viscous mobile liquid.

EXAMPLE 8

- 15 Citric acid monohydrate (150g, 0.71 moles) was dissolved in warm water (104.5g) by heating in a 2 litre fishbowl flask fitted with stirrer, condenser and thermometer. To the stirred solution was added slowly tetra(n-butyl)titanate (97g, 0.28 moles) from a dropping funnel. A butanol/water mixture was removed by distillation at about 80 – 90 °C under vacuum. The product was cooled to about 60 °C and 5% wt/wt aqueous Mg(OH)₂ (292g, 0.25 moles) and 1,3-propanediol (173.5g, 2.28 moles) were
- 20 added slowly by dropping funnel to the stirred solution. The resulting product was refluxed for 1 hour under vacuum to remove butanol/water. The product was then filtered to provide a clear viscous mobile liquid.

EXAMPLE 9

- 25 Water (52.25g, 2.90 moles) and citric acid monohydrate (75g, 0.36 moles) were placed into a pre-weighed rotary evaporator flask, and heated for 15 minutes to dissolve the citric acid. The solution was allowed to cool. A vacuum was applied to the flask and titanium (IV) n-butoxide (48.5g, 0.14 moles) added via vacuum inlet. An azeotrope of n-butanol/water was removed under reduced pressure. The resulting mixture was allowed to cool before the dropwise addition of 5% magnesium
- 30 hydroxide in water (145g, 0.125 moles). 1,4-butanediol (103 g, 1.14 moles) was then added dropwise, whilst stirring. An azeotrope of n-butanol/water was removed under reduced pressure. The resulting mixture was allowed to cool before 50% dilution with 1,4-butanediol to yield a slightly hazy solution with a titanium content of 1.54%.

EXAMPLE 10

Example 9 was repeated except that 5% lithium hydroxide in water (105g, 0.125 moles) was added in place of the magnesium hydroxide. The resulting mixture was allowed to cool before 50% dilution

with 1,4-butanediol to yield a slightly hazy solution with a titanium content of 1.33%.

EXAMPLE 11

5 Example 9 was repeated except that 5% aluminium acetate ($(\text{CH}_3\text{CO}_2)_2\text{AlOH}$) in water (408g, 0.125 moles) was added in place of the magnesium hydroxide. The resulting mixture was allowed to cool before 50% dilution with 1,4-butanediol to yield a slightly hazy solution with a titanium content of 1.84%.

EXAMPLE 12

10 Example 9 was repeated except that 5% zinc oxide in water (203, 0.125 moles) was added in place of the magnesium hydroxide. The resulting mixture was allowed to cool before 50% dilution with 1,4-butanediol to yield a slightly hazy solution with a titanium content of 2.10%.

EXAMPLE 13

15 Example 9 was repeated except that 5% caesium carbonate in water (407g, 0.125 moles) was added in place of the magnesium hydroxide. The resulting mixture was allowed to cool before 50% dilution with 1,4-butanediol to yield a slightly hazy solution with a titanium content of 1.71%.

EXAMPLE 14

20 A 50% w/w aqueous citric acid solution (577 g, 1.5 moles citric acid) was put in a flask. To the stirred solution was slowly added titanium isopropoxide (284g, 1 moles). This mixture was heated to reflux for 1 hour to yield a hazy solution and heated under vacuum to remove free water and isopropanol. The product was cooled below 70°C and 32 %w/w aqueous sodium hydroxide (125 g, 1 moles) was added slowly to the stirred solution. The product was filtered, mixed with ethylene glycol (496 g, 8
25 moles) and heated under vacuum to remove free water/isopropanol. The product was a slightly hazy, very pale yellow liquid (Ti content 5.0 % by weight).

EXAMPLE 15

30 A 50% aqueous citric acid solution (548.5g, 1.4 moles of citric acid) was put in a 1 litre fishbowl flask fitted with stirrer, condenser and thermometer. To the stirred solution was added slowly tetra(n-butyl)titanate (194g, 0.57 moles) from a dropping funnel. An n-butanol/water mixture was removed by distillation at about 80 – 85 °C under vacuum. The product was cooled to around 60 C and 5% wt/wt aqueous NaOH (626g, 0.78 moles) was added slowly by dropping funnel to the stirred solution. The resulting product was cooled, then mixed with 1,4-butanediol (180g, 2.0 moles) and heated under
35 vacuum to remove n-butanol/water. The product was a clear mobile liquid.

EXAMPLE 16

A 50% aqueous citric acid solution (548.5g, 1.4 moles of citric acid) was put in a 1 litre fishbowl flask fitted with stirrer, condenser and thermometer. To the stirred solution was added slowly tetra(n-butyl)titanate (340g, 1 mole) from a dropping funnel. A n-butanol/water mixture was removed by distillation at about 80-85°C. The product was cooled to around 60c and 5% w/w aqueous NaOH (626g, 0.78 moles) was added slowly by dropping funnel to the stirred solution. The resulting product was cooled, then mixed with 1,4-butanediol (180g, 2 moles) and heated under vacuum to remove n-butanol/water. The product was a clear mobile liquid.

EXAMPLE 17 (COMPARATIVE)

The procedure of Example 15 was followed but using 132.5 g, (0.63 moles) of citric acid, 72.0 g, (0.25 moles) of titanium isopropoxide, 94.9 g, (0.76 moles) of 32 %w/w aqueous sodium hydroxide and 125.5 g, (2.0 moles) of ethylene glycol. The product was a slightly hazy, very pale yellow liquid (Ti content 3.85 % by weight).

The catalyst compositions in Examples 1 – 17 are summarised in Table 1.

Table 1

Example	Titanate	Base	$\frac{\text{mols base}}{\text{mols acid}}$	Diol	$\frac{\text{mols diol}}{\text{mols Ti}}$
1*	TIPT	NaOH	1.20	1,4-butane diol	8
2	TNBT	NaOH	0.53	1,4-butane diol	8
3	TNBT	NaOH	0.34	1,4-butane diol	8
4	TNBT	NaOH	0.35	1,4-butane diol	12.4
5	TIPT	NaOH	0.35	1,4-butane diol	8.1
6	TNBT	NaOH	0.35	1,3-propane diol	8.1
7	TNBT	NaOH	0.35	1,3-propane diol	8.1
8	TNBT	Mg(OH) ₂	0.35	1,3-propane diol	8.1
9	TNBT	Mg(OH) ₂	0.35	1,4-butane diol	8.1
10	TNBT	LiOH	0.35	1,4-butane diol	8.1
11	TNBT	(CH ₃ CO ₂) ₂ AlOH	0.35	1,4-butane diol	8.1
12	TNBT	ZnO	0.35	1,4-butane diol	8.1
13	TNBT	Cs ₂ CO ₃	0.35	1,4-butane diol	8.1
14	TIPT	NaOH	0.67	1,2-ethane diol	8
15	TNBT	NaOH	0.56	1,4-butane diol	3.5
16	TNBT	NaOH	0.56	1,4-butane diol	2.0
17*	TIPT	NaOH	1.21	1,2-ethane diol	8

Notes:

* = Comparative,

TNBT = tetra n-butyl titanate

TIPT = tetra isopropyl titanate

5

EXAMPLE 18 Preparation of PBT from dimethyl terephthalate

1,4-butanediol (58 g) and dimethyl terephthalate (46.5 g) were charged to a jacketed reactor and maintained at a temperature of 160 °C. The catalyst TNBT (tetra(n-butyl) titanate) or a catalyst made in one of the preceding examples was added and the reactor heated to 210 – 260 °C to initiate the first stage interesterification process and continued until all of the methanol had been removed. On completion of the DE reaction the pressure was reduced to 1 mbar and the mixture maintained at 260 °C under vacuum to remove 1,4-butanediol and yield polybutylene terephthalate. After 70 minutes of polymerisation time, the product polymer had an intrinsic viscosity (IV) (as measured by solution viscosity on an 8% solution of the polyester in o-chlorophenol at 25°C) of 0.932.

15

Table 2

Catalyst	Ti ppm	PC mins	P (ppm)	Colour			IV dl/g
				L*	a*	b*	
TNBT	160	70	-	68.48	-1.29	-0.65	0.932
Example 3	160	70	-	78.33	-1.36	1.79	0.915
Example 3	160	70	2*	82.5	-1.03	2.8	0.79
Example 4	160	70	-	74.77	-0.72	0.68	0.612
Example 9	160	70	-	68.50	-1.14	3.62	0.882
Example 10	160	70	-	65.65	-1.35	0.72	0.661
Example 11	160	70	-	79.06	-0.65	2.37	0.603
Example 12	160	70	-	72.43	-0.79	1.46	0.765
Example 13	160	70	-	62.50	-1.16	-2.80	0.668

*phosphorus added as Irganox™ 1222.

The colour of the polymer was measured using a Byk-Gardner Colourview spectrophotometer. A common model to use for colour expression is the Cielab L*, a* and b* scale where the b*-value describes yellowness. The yellowness of the polymer increases with b*-value.

20

The results are shown in Table 2.

EXAMPLE 19 Preparation of PBT from terephthalic acid

The catalyst prepared in Example 3 was used to prepare polybutylene terephthalate (PBT). 1,4-butanediol (2.907kg) and terephthalic acid (3.154kg) were charged to a jacketed reactor and

25

maintained at a temperature of 160 °C. The catalyst (18.62g, 90ppm Ti w/w on final polymer) was added and the reactor heated to 210 – 260 °C to initiate the first stage esterification process and continued until all of the water had been removed. On completion of the direct esterification (DE) reaction, the pressure was reduced to 1 mbar and the mixture maintained at 260 °C under vacuum to remove 1,4-butanediol by polycondensation (PC) and yield polybutylene terephthalate. A comparison process was run using TNBT as a catalyst.

Table 3

Catalyst	Ti ppm	DE mins	PC mins	L	a*	b*	IV dl/g	CEG meq/g
TNBT	90	72	178	89.51	-1.15	4.64	0.94	16.3
Example 3	90	55	160	89.49	-0.81	7.52	0.94	16

EXAMPLE 20 Preparation of Poly(ethylene terephthalate) (PET)

Ethylene glycol (2.04 kg), isophthalic acid (125g) and terephthalic acid (4.42 kg) were charged to a stirred, jacketed reactor. The catalyst was added and the reactor heated to 226 - 252 °C at a pressure of 40 psi to initiate the first stage direct esterification (DE) process. Water was removed as it was formed with recirculation of the ethylene glycol. On completion of the DE reaction the contents of the reactor were allowed to reach atmospheric pressure before a vacuum was steadily applied. A phosphorus-containing stabiliser and cobalt acetate were added and the mixture heated to 290 ± 2 °C. under vacuum to remove ethylene glycol and yield polyethylene terephthalate. The final polyester was discharged once a constant torque had been reached which indicated an IV of about 0.62.

The crystallisation behaviour of the resulting PET polymer was investigated using differential scanning calorimetry (DSC). A 10mg specimen was dried overnight under vacuum at 80°C. The dried specimen was heated at 290°C for 2 minutes in the Perkin-Elmer DSC7A before being quench-cooled, onto a cold block. The quenched specimen was then heated from 0°C to 290°C at a rate of 20°C/minute, held at that temperature for 2 minutes, cooled back to 0°C, held for 2 minutes then reheated. A correction of +3.1°C has been applied to the computer generated cooling temperature data.

The catalysts used, and the results are shown in Table 4. The results show that the temperatures for onset of crystallisation (T_{n0}) and crystallisation (T_n) are higher for the polyester produced using the catalyst of the invention in which the ratio of base to acid is 1.12, than for the polyester produced with the comparative catalyst in which the ratio of base to acid is 0.67 although the melting points are the same. These results provide evidence that the catalysts of the prior art, containing higher levels of base, induce faster crystallisation. The fabricator of e.g. polyester film may find a wider thermal

processing window using polyester made with catalysts of the invention because crystallisation is slower.

Table 4

Catalyst	Initial Heat (sample dried and quenched)					
	T _g °C	T _n °C	T _n °C	ΔH J/g	T _p °C	ΔH J/g
Example 14	75	150	165	-36	246	36
Example 17 (comparative)	77	145	162	-36	246	35

Claims

1. A catalyst composition comprising the reaction product of an alkoxide or condensed alkoxide of a metal M, selected from titanium, zirconium, hafnium, aluminium, or a lanthanide, an alcohol containing at least two hydroxyl groups, a 2-hydroxy carboxylic acid and a base, wherein the molar ratio of base to 2-hydroxy carboxylic acid is in the range 0.01 – 0.79:1.
2. A catalyst composition as claimed in claim 1, wherein the alcohol is selected from the group consisting of 1,2-ethanediol, 1,2-propanediol, 1,3-propanediol, 1,4-butane diol, diethylene glycol and a polyethylene glycol.
3. A catalyst composition as claimed in either claim 1 or claim 2, wherein the 2-hydroxy carboxylic acid comprises lactic acid, citric acid, malic acid or tartaric acid.
4. A catalyst composition as claimed in any of the preceding claims, wherein the molar ratio of acid to metal in the reaction product is from 1 to 4 moles acid per mole of metal M.
5. A catalyst composition as claimed in any of the preceding claims, wherein the base comprises sodium hydroxide, potassium hydroxide, ammonium hydroxide, lithium hydroxide, sodium carbonate, magnesium hydroxide, calcium hydroxide, aluminium acetate, zinc oxide, caesium carbonate or ammonia.
6. A catalyst composition as claimed in any of the preceding claims, wherein the metal M is selected from titanium and zirconium.
7. A process for the preparation of an ester comprising carrying out an esterification reaction in the presence of a catalyst composition as claimed in any of the preceding claims.
8. A process as claimed in claim 7 wherein said esterification reaction comprises the reaction of an acid or anhydride selected from stearic acid, isostearic acid, capric acid, caproic acid, palmitic acid, oleic acid, palmitoleic acid, triacontanoic acid, benzoic acid, methyl benzoic acid, salicylic acid, phthalic acid, isophthalic acid, terephthalic acid, sebacic acid, adipic acid, azelaic acid, succinic acid, fumaric acid, maleic acid, naphthalene dicarboxylic acid, pamoic acid, trimellitic acid, citric acid, trimesic acid, pyromellitic acid and anhydrides of these acids with an alcohol selected from butyl, pentyl, hexyl, octyl and stearyl alcohols, 2-ethylhexanol, glycerol and pentaerythritol.
9. A process as claimed in claim 7 wherein said esterification reaction is a polyesterification reaction comprising the reaction of one or more polybasic acids or esters of polybasic acids one or more polyhydric alcohols to produce a polymeric ester.

10. A process as claimed in claim 9, wherein said polyesterification reaction comprises the reaction of terephthalic acid or dimethyl terephthalate with 1,2-ethanediol (ethylene glycol) to produce polyethylene terephthalate, with 1,3-propane diol to form poly(trimethylene)terephthalate, or with 1,4-butanediol (butylene glycol) to produce polybutylene terephthalate (PBT) or the reaction of naphthalene dicarboxylic acid with 1,2-ethanediol to produce polyethylene naphthalate (PEN).

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
17 June 2004 (17.06.2004)

PCT

(10) International Publication Number
WO 2004/050239 A3

(51) International Patent Classification⁷: **C07C 67/08**,
67/03, B01J 27/236, 31/38

(21) International Application Number:
PCT/GB2003/005180

(22) International Filing Date: 1 December 2003 (01.12.2003)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
0228267.1 4 December 2002 (04.12.2002) GB

(71) Applicant (for all designated States except US): **JOHNSON MATTHEY PLC** [GB/GB]; 2-4 Cockspur Street, Trafalgar Square, London SW1Y 5BQ (GB).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **LINDALL, Charles, Mark** [GB/AU]; 94 Pindari Avenue, Camden, NSW 2570 (AU). **SLACK, Neville** [GB/GB]; 139 Station Road, Billingham, Stockton-on-Tees, Cleveland TS23 2RL (GB). **PARTRIDGE, Martin, Graham** [GB/GB]; 33 Houghton Banks, Ingleby Barwick, Stockton-on-Tees, Cleveland TS17 5AL (GB).

(74) Agents: **GIBSON, Sara, Hillary, Margaret et al.**; Intellectual Property Department, Johnson Matthey Catalysts, P.O. Box 1 Belasis Avenue, Billingham, Cleveland TS23 1LB (GB).

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (*regional*): ARIPO patent (BW, GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

- with international search report
- before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments

(88) Date of publication of the international search report:
16 September 2004

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: CATALYST AND PROCESS

(57) Abstract: A catalyst composition comprises the reaction product of an alkoxide or condensed alkoxide of a metal M, selected from titanium, zirconium, hafnium, aluminium, or a lanthanide, an alcohol containing at least two hydroxyl groups, a 2-hydroxy carboxylic acid and a base, wherein the molar ratio of base to 2-hydroxy carboxylic acid is in the range 0.01 - 0.79:1. The composition is useful as a catalyst for esterification reactions, especially for the production of polyesters such as polyethylene terephthalate, polytrimethylene terephthalate and polybutylene terephthalate.

WO 2004/050239 A3

INTERNATIONAL SEARCH REPORT

International Application No

PCT/GB 03/05180

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C07C67/08 C07C67/03 B01J27/236 B01J31/38

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C07C B01J

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the International search (name of data base and, where practical, search terms used)

EPO-Internal

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 1 120 392 A (ACMA LTD) 1 August 2001 (2001-08-01) the whole document ----	1-10
X	EP 0 812 818 A (TIOXIDE SPECIALTIES LTD) 17 December 1997 (1997-12-17) the whole document ----	1-10
X	GB 2 314 081 A (TIOXIDE SPECIALTIES LTD) 17 December 1997 (1997-12-17) cited in the application the whole document -----	1-10

☐

Further documents are listed in the continuation of box C.

☒

Patent family members are listed in annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the International filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

25 June 2004

Date of mailing of the international search report

13/07/2004

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Klaes, D

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/GB 03/05180

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 1120392	A	01-08-2001	EP 1120392 A1 01-08-2001
		AT 254096 T	15-11-2003
		AT 207866 T	15-11-2001
		AU 730131 B2	22-02-2001
		AU 2363597 A	18-12-1997
		BR 9703577 A	10-11-1998
		CA 2207111 A1	11-12-1997
		CN 1169412 A ,B	07-01-1998
		CZ 9701762 A3	13-05-1998
		DE 69707757 D1	06-12-2001
		DE 69707757 T2	25-04-2002
		DE 69726200 D1	18-12-2003
		DE 69726200 T2	15-04-2004
		DK 812818 T3	19-11-2001
		EP 0812818 A1	17-12-1997
		ES 2166505 T3	16-04-2002
		GB 2314081 A ,B	17-12-1997
		HU 9701024 A2	02-03-1998
		JP 10081646 A	31-03-1998
		NO 972645 A	12-12-1997
		PL 320469 A1	22-12-1997
		PT 1120392 T	30-04-2004
		PT 812818 T	28-02-2002
		RU 2178783 C2	27-01-2002
		TR 9700487 A2	21-12-1997
		US 5866710 A	02-02-1999
EP 0812818	A	17-12-1997	AT 254096 T 15-11-2003
			AT 207866 T 15-11-2001
			AU 730131 B2 22-02-2001
			AU 2363597 A 18-12-1997
			BR 9703577 A 10-11-1998
			CA 2207111 A1 11-12-1997
			CN 1169412 A ,B 07-01-1998
			CZ 9701762 A3 13-05-1998
			DE 69707757 D1 06-12-2001
			DE 69707757 T2 25-04-2002
			DE 69726200 D1 18-12-2003
			DE 69726200 T2 15-04-2004
			DK 812818 T3 19-11-2001
			EP 1120392 A1 01-08-2001
			EP 0812818 A1 17-12-1997
			ES 2166505 T3 16-04-2002
			GB 2314081 A ,B 17-12-1997
			HU 9701024 A2 02-03-1998
			JP 10081646 A 31-03-1998
			NO 972645 A 12-12-1997
			PL 320469 A1 22-12-1997
			PT 1120392 T 30-04-2004
			PT 812818 T 28-02-2002
			RU 2178783 C2 27-01-2002
			TR 9700487 A2 21-12-1997
			US 5866710 A 02-02-1999
GB 2314081	A	17-12-1997	AT 254096 T 15-11-2003
			AT 207866 T 15-11-2001
			AU 730131 B2 22-02-2001
			AU 2363597 A 18-12-1997

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/GB 03/05180

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
GB 2314081	A	BR 9703577 A	10-11-1998
		CA 2207111 A1	11-12-1997
		CN 1169412 A , B	07-01-1998
		CZ 9701762 A3	13-05-1998
		DE 69707757 D1	06-12-2001
		DE 69707757 T2	25-04-2002
		DE 69726200 D1	18-12-2003
		DE 69726200 T2	15-04-2004
		DK 812818 T3	19-11-2001
		EP 1120392 A1	01-08-2001
		EP 0812818 A1	17-12-1997
		ES 2166505 T3	16-04-2002
		HU 9701024 A2	02-03-1998
		JP 10081646 A	31-03-1998
		NO 972645 A	12-12-1997
		PL 320469 A1	22-12-1997
		PT 1120392 T	30-04-2004
		PT 812818 T	28-02-2002
		RU 2178783 C2	27-01-2002
		TR 9700487 A2	21-12-1997
		US 5866710 A	02-02-1999